

BYLAPOX 5 Min EP

Type	Fast curing epoxy-system, 5 minutes
Application	Bonding of metals, wood, many plastics, china, etc.
Mixing ratio	1 : 1
Density	1,1 g/ml
Viscosity at 25°C	Part <A>: max. 9.000 mPas, Part : max. 14.000 mPas
Pot life	2 - 3 minutes
Shelf life at RT	1 year
Containers	PE bottles 100 ml each Bylamix 2K50 with 50 ml (25 ml/component) Bylamix 2K400 with 400 ml (200 ml/component) drums with 25 kg drums with 200 kg

Tensile shear strength DIN 53283 on steel

Curing time	Strength [N/mm ²]
10 min	1
15 min	5
30 min	11
1 h	13
4 h	15
3 days	25

Above stated instructions are indicative only and no responsibility can be assumed. We recommend to check suitability of our products for your purpose by doing tests on your own.

BYLA GmbH Industriestraße 12 D-65594 Runkel	Telefon +49/(0)6482/91200 Telefax +49/(0)6482/912011	Internet: http://www.byla.de eMail: contact@byla.de
---	---	--