

BYLA MET 99

Description:	One component cyanoacrylate adhesive based on modified ethylenester, low viscous		
Application:	Bonding of plastics, rubber, metals.		
Specials:	Bonds in seconds rubbers and plastics.		
Colour:	colourless		
Viscosity:	20 ~ 30 mPas		
Density:	1,05 g/ml		
Temperature range:	-50° to +80° C		
Handling strength:	Rubber:	1 ~ 5 sec	
	Metals:	1 ~ 15 sec	
	Plastics:	1 ~ 5 sec	
Tensile shear strength	Steel/Steel:	17 N/mm ²	
Max. gap:	0,05 mm		

Above stated instructions are indicative only and no responsibility can be assumed. We recommend to check suitability of our products for your purpose by doing tests on your own.