

SigaMent VE 640

2-C-vinyl ester resin mortar

Empowered by Expertise!

Description: **SigaMent VE 640** is a two-component, cold curing synthetic resin mortar, based on a Novolac vinyl ester resin with mineral fillers.

- Characteristics:**
- Very good mechanical resistance
 - Very good chemical resistance, especially against oxidizing media, as well as many organic compounds
 - Fast curing

Applications: **SigaMent VE 640** is suitable for bedding and jointing of tiles, bricks and fittings, especially for chemical loads of acids, solvents and oxidizing medium. Furthermore, **SigaMent VE 640** has a good resistance against high temperatures and high mechanical stresses. Main application fields are tiling and brick linings of components in the chemical industry, waste water and process water treatment, pulp and paper industry and pickling lines.

Chemical resistance: Information on the chemical resistance is available on request.

Substrate: Components shall be designed and manufactured in accordance with EN 14879-1. Before start of brick lining work, the suitability of the surface preparation measures according EN 14879-1 must be checked and recorded.

Pot life (20°C):

Product	Time (min)
SigaMent VE 640	ca. 40

Curing (20°C):

Load Capacity	Time
Accessible	ca. 24 h
Chemical load	ca. 2 Days

Packaging: The products are supplied in the following standard package sizes:

Product	Size	Article No.
SigaMot H 910	0.1 kg	592 0455
SigaMot H 910	0.4 kg	592 0450
SigaMent VE 640 SOLUTION	20 kg	592 0350
SigaMent VE 640 POWDER	25 kg	592 0360
SigaMent VE 640 UNI	8.4 kg	592 0900

Storage: The products must be stored in a cool and dry place, away from direct sunlight. At the specified storage temperatures a shelf life of the products is given of at least for the following periods:

Product	Temperature	Shelf Life
SigaMot H 910	≤ +20°C	12 Months
SigaMent VE 640 UNI	≤ +20°C	24 Months
SigaMent VE 640 SOLUTION	≤ +20°C	3 Months
SigaMent VE 640 POWDER	-	24 Months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof. In addition, the DIN 7716 must be observed.

1. Surface preparation

Steel and concrete surfaces must be primed before application. The primer must be sanded in a fresh state after the final coat. Sealing layers, except VE or UP based layers, must be provided with a sanded primer before application of the synthetic mortar. Unevenness should be compensated in the ground.

C-STEEL

All contaminants, including non-visible detectable contaminants, must be removed in accordance with DIN Fachbericht #28 and EN ISO 8502.

Ferrite steel surfaces shall be abrasive blasted to "Near White Metal" in accordance with EN ISO 12944-4. A standard preparation degree of SA 2½ (SSPC SP-10; NACE #2) as specified in EN ISO 8501-1 must be achieved. The primer must be applied immediately after the blasting.

CONCRETE

Appropriate action shall be taken to prepare the concrete surfaces; dry and free of dust and free of contaminants such as oil or grease. The concrete shall have minimum tensile strength of 1.5 N/mm². The residual moisture content must not exceed 4%.

2. Environmental conditions

The specified environmental conditions must be observed during surface

preparation and brick lining and be tested and recorded according EN 14879-6.

Environmental conditions	Value
Relative Humidity	≤ 80%
Surface Temperature	≥ +10°C up to +30°C
Application Temperature	+20°C ± 5°C recommended
Dew Point Distance	min. 3K

3. Application

The execution of the brick lining work is only permitted, if the requirements of "Surface Preparation" and "Environmental Conditions" are met.

SigaMent VE 640 is applied on the substrate or sealing layer by using a mortar trowel. Tiles and bricks must be free of voids, fully bedded and hollow jointed.

4. Work tools

The following tools are essential for the application:

- Stirrer (max. 300 r/min.)
- Measuring cup & Mixing vessels
- Flat / wide brush
- Mortar trowel
- Grouting tool
- Miscellaneous (safety glasses, rubber gloves etc.)

5. Mixing ratio

Pour **SigaMent VE 640 SOLUTION** in a mixing vessel and add **SigaMent VE 640 POWDER** at the specified mixing ratio. The stirring of the merged components should

be at least 3 minutes and must result in a homogeneous mixture.

Primer	kg per litre	Parts by Weight	Parts by Volume
SigaMent VE 640 SOLUTION	1.000	100	1.000
SigaMot H 910	0.020	2	0.020

SigaMent VE 640	kg per litre	Parts by Weight	Parts by Volume
SigaMent VE 640 SOLUTION	0.429	100	1.000
SigaMent VE 640 POWDER	1.371	320	2.450

6. Consumption

Bedding and jointing (Bed Joint 5 mm / Cross joint 5-7 mm)

Material	Sizes (mm)	Coverage (kg/m ²)
Tiles	240 x 115 x 20	ca. 15
Tiles	240 x 115 x 40	ca.17
Bricks	240 x 115 x 65	ca.20
Bricks	240 x 115 x 80	ca.22

7. Cleaning

Clean all equipment with **SigaMent VE 640 UNI** immediately after use. The cleaning is done while the material is still not hardened.

8. Safety measures

The material safety data sheets of the individual components, the safety instructions on the packing (label) as well as the legal requirements for handling hazardous materials must be observed.

Technical Data	Standard	Unit	Value
Resistance to Ground	DIN 14879-6	Ω	> 10 ⁹
Density (Mixture)	EN ISO 2811 (ASTM D1475)	g/cm ³	1.8
Compressive Strength	EN ISO 604	N/mm ²	80
Coefficient of Thermal Expansion	-	1/K	35 x 10 ⁻⁶
Max. Operating Temperature Liquids	-	°C	+ 150

Note: The indicated temperatures are dependent on the present load and may vary

SigaMent VE 640; 0.00/28.08.2017. All information contained herein is based on the current state of our knowledge and practical experience at the time of release. Therefore, please make sure that this is the actual edition of the Technical Data Sheet. All data are only intended as a guideline for informational purposes and do not constitute a legally-binding warranty of the suitability for a certain purpose of use, due to its dependence on site conditions and possible processing, use and applications. All information contained in this technical datasheet is subject to change without notice.

SIGAS GmbH
Huttropstr. 60
45138 Essen
Germany
Tel: +49 201 17003 270
Fax: +49 201 17003 277
E-Mail: info@sigas.de
Web: www.sigas.de