

BYLLOC 302

Description: Bylloc 302 cures fast and reliable under the absence of air with high strength. It is resistant against the most solvents.

Application: High strength threadlocking of screws, large bolts and studs.

Physical Data:

Colour: Green
Dry Content: 100 %
Viscosity: 600 ~ 1.000 mPas
Flash Point: > 100° C
Density: 1,1 g/ml
Max. Gap: max. 0,15 mm
Breakloose: > 35 Nm (M10)
Compressive Shear Strength: > 20 N/mm²
Cure Speed: Handling Strength: 15 min Final Strength: 24 h
Temperature Resistance: -50 ~ +150° C

Pre-treatment: Parts must be clean, free of oil and fat.

Shelf Life: 12 months at room temperature in original containers.

Containers: Bottles with 50 g und 250 g

Health and Safety: The material may cause allergic reaction of skin. Therefore contact to skin should be avoided. If there is contact to the eyes spoil with a sufficient amount of water and attend a physician. Take care for good ventilation, do not inhale vapour!

Above stated instructions are indicative only and no responsibility can be assumed. We recommend checking suitability of our products for your purpose by doing tests on your own.